

## MECHANICAL PROPERTIES

Alloy Name			Mechanical Properties	
			Tensile Strength N/mm <sup>2</sup> (kgf/mm <sup>2</sup> )	Compression strength N/mm <sup>2</sup> (kgf/mm <sup>2</sup> )
Co Base	Bishilite (MHA)	NO.1	760(78)	1580(161)
		NO.6	920(94)	1700(173)
		NO.12	970(99)	1780(181)
		NO.21	800(82)	2010(205)
		NO.32	770(79)	2000(204)
		NO.1016	620(63)	1650(168)
	MHA NO.800	690(71)	1780(181)	
NI Base	MHA NO.700	470(48)	1450(148)	
Iron Base	MA-CS	1030(105)	2540(259)	

BISHILITE: MMCSA Hard Facing Alloy

The data above are test samples, and do not guarantee maximum or minimum values

Contact us for more information.

Sales & Marketing Div.	TEL : +81-48-786-3709	<a href="#">Inquiry form</a>
------------------------	-----------------------	------------------------------